

Technical Datasheet
Europe

COATING	GS	J3092
		Version 10 Status Standard Updated 7/2/2017 Issued on 5/9/2019
Product	Description	Internal lacquer
	End use	Collapsible tubes
	Typical properties	Retortable
	Resin type	Epoxy phenolic
	Solution form	Solvent based
	Colour	Gold
Specification	Viscosity	34 - 41 sec. DIN 4 @ 23 °C
	Dry solids	31.5 - 35.5% 0.2g 10 Mins @ 190°C
	Refractive index	
	Specific gravity	Wet 1.010 ± 0.05
Application	Application method	Spraying
	Substrate	Aluminium
	Application viscosity	34 - 41 sec. DIN 4 @ 23 °C
	Thinners	V1032
	Wash up solvents	V1032
	Filmweight	7 - 11 microns Dry
	Curing conditions	3-6 min. @ 220-260 °C Oven curing
	Advice	Performance should be confirmed under actual line conditions Interior products should be pack tested to confirm suitability for end use
Remarks	Shelf life: 6 months	Between 5-30°C  Do not directly expose to sun or heat  Stir well before use

H401F056 6074010056

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Sherwin-Williams assumes no obligation or liability for use of this information. UNLESS SHERWIN-WILLIAMS AGREES OTHERWISE IN WRITING, SHERWIN-WILLIAMS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. SHERWIN-WILLIAMS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. The information in this sheet (if marked as "Confidential"), as well as the products referenced herein, shall be considered "Confidential Information." Wet samples and uncured samples of these products shall be maintained as confidential and shall not be disclosed to any third party without the prior written permission of Sherwin-Williams. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.

The Valspar (Switzerland) Corp. AG, a member of the Sherwin-Williams Company, Industriestrasse 9, CH-8627 Grüningen, Switzerland

